

PLANO CONTACT FAST

Bonding primer for non-absorbent surfaces

- ▷ **Water-based, VOC and APEO free**
 - ▷ **Can be coated quickly**
 - ▷ **Excellent alkaline resistance**
 - ▷ **Very high adhesion and scrub resistance**
 - ▷ **Resistance to water and ageing**
-

Description

PLANO CONTACT is a ready to use primer composed of synthetic resin in water dispersion with quartz sand. It has excellent adhesion even on very smooth substrates and substrates with low absorbency. It creates a rough surface very quickly and ensures with a waiting time of 15 - 60 minutes the adhesion of the coating that follows. Meets the requirements of REACH legislation without APEO.

Uses

PLANO CONTACT can be used on:

- Internal and external floors and walls
- On smooth substrates and substrates with low absorbency surfaces such as old ceramic, terrazzo, natural stones, glass and metal
- Concrete, gypsum and cement boards, thermal insulating panels
- Old paints

It creates suitable adhesion conditions for:

- All types of cement, gypsum, lime-based and acrylic plasters
 - Tile adhesives, smoothing and leveling compounds
 - Decorative coatings and microcement of the PLANOCOLOR system
-

Technical Data

Product Identity

Form	Creamy liquid
Color	Pink - beige
Chemical substance	Acrylic dispersion
Density	1,45 ± 0,05 kg/L
Application temperature	+5°C to +35°C
Waiting time before applying coating	15 – 60 minutes

Application Procedure

Substrate Preparation Substrates must be clean, dry, well-cured and free from oil, grease, cement laitance and loose parts.

Application Before applying stir the contents of the container until a homogenous mixture. PLANO CONTACT FAST may be applied to the substrate by brush or by roller. Once dry you can apply the plaster or mortar. The waiting time varies depending on the environmental conditions and absorbency of the substrate. For light absorbent surfaces it can be diluted up to 10% with water.

Recommendations Avoid using PLANO CONTACT FAST:

- In cases where the substrate and environment temperature is less than +5°C or higher than +35°C as well the relative humidity is greater 80%
- on wet substrates

Also note the following:

- Never exceed the maximum recommended quantity of mixing water (10%)
- Protect the tilled surface from rain and frost for the first 1 hour
- Application should be performed by professional user

Consumption 0,3 – 0,4 kg/m²

Storage To PLANO CONTACT remains stable for 12 months from production date inside its original sealed packaging, stored in protected dry area in temperatures between +5°C and +35°C.

Packaging 5 and 15 kg buckets.

Safety Instructions

For information and instructions regarding disposal and safe handling, users should refer to the latest Safety Data Sheet of the product containing ecological, toxicological and other safety related data.

Legal notes

The technical data and recommendations included or listed are the outcome of laboratory measurements combined with our current knowledge and expertise. All information and specifications should in any case be considered as indicative. The Company makes every effort to ensure the accuracy of the information provided herein. Product specifications are subject to change without notice and may differ from product images. Due to printing and application procedures, the colors displayed here should be considered as indicative. In particular, variations in materials, substrates and on-site application conditions are such that no warranty can be given or implied reference to the suitability of the materials for trading or use for a particular purpose and conditions of any given project. Anyone interested in using the product must ensure beforehand that the product is suitable for the intended use and in any case, the user is solely responsible for any outcomes associated with the use of product. Among other things, the Company is not responsible for any normal wear or tear from environmental or any other unsuitable conditions. We reserve the right to revise or change the data herein without prior notice. Restrictions and disclaimers apply to the extent permitted by applicable law. The Company has a Technical Support Department, which has exclusive responsibility for providing technical advice and solutions, addressing relevant issues. Requests to the Technical Support Department are addressed and answered, only in writing. For the latest and valid version of the Technical Data Sheet, the user of the material must refer to our website www.novamix.gr.



DOMOCHEMICAL S.A.
40 Papanikoli str.
Chalandri, 15232, Athens
T +30 210 68 93 953
F +30 210 68 94 571
novamix@novamix.gr