

PRODUCT DATA SHEET

SikaCor[®]-146 DW

EPOXY COATING FOR USE IN THE POTABLE WATER SUPPLY, 100 % VOLUME SOLIDS



DESCRIPTION

SikaCor[®]-146 DW is a fast-curing 2-pack epoxy coating for steel and concrete. The coating is tough elastic, mechanically resistant and resistant to abrasion, impact and shock. Solvent free according to Protective Coatings Directive of German Paint Industry Association (VdL-RL 04).

USES

SikaCor[®]-146 DW may only be used by experienced professionals. SikaCor[®]-146 DW is ideally suited for the corrosion protection of surfaces such as steel, stainless steel and aluminium, and for the protection of mineral surfaces made of concrete and cement plaster in direct contact with media. SikaCor[®]-146 DW is predominantly used as an interior coating for tanks, silos, containers, pipes (nominal diameter > 300 mm) and equipment used in potable water supply as well as in the food and beverage industry.

CHARACTERISTICS / ADVANTAGES

- Suitable for potable water, many foodstuffs, chemicals, cleaning agents and disinfectants
- Very good adhesion to steel, stainless steel, aluminium and concrete
- Economical one-coat application
- No extensive post-treatment before initial filling
- Pinhole detection possible on metallic surfaces
- Contains no benzyl alcohol

APPROVALS / CERTIFICATES

- Coating based on epoxy resin for concrete protection according to EN 1504-2, DoP, with CE mark.
- Conforms to the coating guideline of the German 'Umweltbundesamt' (UBA = Federal Environment Agency) in contact with potable water.
- Tested according to DVGW (German Association for Gas and Water) worksheet W 270 (growth of microorganisms in potable water).
- Physiologically harmless (expert report by Nehring Institute).
- Monitored by KIWA NL in accordance with BRL-K 759 as a certified coating for contact with potable water.

PRODUCT INFORMATION

Packaging	SikaCor [®] -146 DW	12.6 kg and 6.3 kg net.
Appearance / Colour	Blue, beige, red brown Finish: Glossy	
Shelf life	24 months from date of production	
Storage conditions	In originally sealed containers in a cool and dry environment.	
Density	~1.35 kg/l	
Solid content	~100 % by volume ~100 % by weight	

TECHNICAL INFORMATION

Chemical Resistance Depending on the medium, available upon request.
No long term resistance to ozone containing media.

Thermal Resistance Dry heat up to approx. + 100°C

SYSTEMS

Systems

Steel, stainless steel and aluminium

Airless application:

1 x 400 µm SikaCor®-146 DW

Roller:

3 x 150 µm SikaCor®-146 DW

Concrete

A) System with polymer cement concrete (PCC) base coat:

2 x Sikagard®-720 EpoCem® mortar (alternatively levelling with SikaTop® TW)

Work 1 x SikaCor®-146 DW well into the substrate – pore-free surface

Apply 1 x SikaCor®-146 DW by airless spraying or

Apply 2 x SikaCor®-146 DW with roller or brush

The practical consumption depends on the surface properties and on the application method.

Concrete repair measures should be carried out using products suitable for potable water. Refer to the product data sheets of Sika MonoTop®-613 and SikaTop® TW regarding this point. Intensive post-treatment (3 - 4 days) must be ensured.

The concrete surfaces must be appropriately prepared before coating with SikaCor®-146 DW. Levelling can also be accomplished with SikaTop® TW. However the base layer has to be Sikagard®-720 EpoCem® mortar. Layer thickness 2-3 mm.

This base layer must be absolutely pore-free. Intensive post-treatment over 4 days. Prior to the coating with SikaCor®-146 DW, the residual moisture content of the substrate must be measured at not more than 4 % by volume using the CM device.

B) System with epoxy base coat:

1 - 2 SikaCor®-146 DW levelling mortar

1 x SikaCor®-146 DW applied by airless spraying

The tensile strength of the concrete substrate should be at least 1.5 N/mm².

The residual moisture content of the substrate must be measured at not more than 4 % by volume using the CM device.

The waiting time until the levelling mortar can be overcoated is the same as for SikaCor®-146 DW.

SikaCor®-146 DW can be used as adhesive for Sikadur-Combiflex® SG-system by adding approx. 4 - 6% by weight of thixotropic agent T. This must be stirred into SikaCor®-146 DW homogeneously. The addition amount is strongly temperature-dependent. Because of the short pot life of SikaCor®-146 DW prepare only the quantities which can be applied in due time.

APPLICATION INFORMATION

Mixing Ratio	Components A : B	
	By weight	100 : 26
	By volume	100 : 39
Consumption	Material consumption on steel	
	Theoretical material-consumption / coverage without loss for medium dry film thickness:	
	Dry film thickness	400 µm
	Wet film thickness	400 µm
	Consumption	~0.54 kg/m ²
	Coverage	~1.85 m ² /kg
	Layer thickness range: At least 300 µm up to max. 800 µm per coat (spraying)	
	Material consumption on concrete	
	<u>A) System with polymer cement concrete (PCC) base coat:</u>	
	Levelling	
	2 x Sikagard®-720 EpoCem®, alternatively	
	1 x SikaTop® TW as scratching / levelling mortar	~2 kg/m ² /mm
	1st layer (work well into the substrate)	
	1 x SikaCor®-146 DW	0.20 - 0.25 kg/m ²
	2nd layer airless sprayed	
	1 x SikaCor®-146 DW	0.60 - 0.80 kg/m ²
	or 2nd / 3rd layer manually by brush or roller	
	2 x SikaCor®-146 DW	0.20 - 0.25 kg/m ² each
	<u>B) System with quartz sand:</u>	
	SikaCor®-146 DW filled with quartz sand and thixotropic agent can be used to prepare the substrate as an alternative to levelling with PCCs.	
	Levelling with SikaCor®-146 DW up to 2 mm	
	1 x SikaCor®-146 DW	~1.00 kg/m ² /mm
+ Quartz sand 0.4 - 0.7 mm	~0.25 kg/m ² /mm	
+ Quartz sand 0.1 - 0.3 mm	~0.25 kg/m ² /mm	
+ thixotropic agent Extender T	~0.06 kg/m ² /mm	
Topcoat airless sprayed		
1 x SikaCor®-146 DW	0.60 - 0.80 kg/m ²	
Levelling with SikaCor®-146 DW up to 4 mm		
1 x SikaCor®-146 DW	~1.00 kg/m ² /mm	
+ Quartz sand 0.4 - 0.7 mm	~0.50 kg/m ² /mm	
+ thixotropic agent Extender T	~0.06 kg/m ² /mm	
Topcoat airless sprayed		
1 x SikaCor®-146 DW	0.60 - 0.80 kg/m ²	
The data for levelling using SikaCor®-146 DW are approximate values and are influenced by the texture and porosity of the surface as well as the surface roughness.		
Ambient Air Temperature	Min. + 15°C	
Relative Air Humidity	Max. 80 %, surface temperature must be at least 3 K above dew point.	
Surface Temperature	Min. + 15°C	

Substrate Moisture Content	Concrete: Max. 4 % by volume (CM-measuring)	
Pot Life	At + 20°C	~20 min
	At + 30°C	~10 min
Curing Time	Curing at + 20°C	
	Touch dry after	~10 h
	Walkable after	~18 h
	Mechanically and chemically loadable after	~7 days
Waiting Time / Overcoating	Min. 8 h at + 20°C	
	Max. 72 h at + 20°C	
	The coating surface must be prepared by sweep-blasting in case of a longer waiting time.	
	Coatability	
	With itself, others on enquiry.	
Drying time	Final drying time	
	10 to 14 days at a substrate temperature of + 20°C.	
	On putting the containers/plant components into operation, local regulations regarding potable water must be observed.	

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

Concrete and cement plaster:

The surface areas to be coated must conform to the building standards and must be capable of bearing loads, firm and free from bond-impairing materials. The average tensile strength according to DIN 1048 should be at least 1.5 N/mm² and must not fall below the lowest individual value of 1.0 N/mm². In the case of high mechanical loads, the average nominal value is 2.0 N/mm² and the lowest individual value 1.5 N/mm². Suitable preliminary coatings compatible with the system are to be used.

The respective overcoating times must be observed.

SURFACE PREPARATION

Steel:

Removal of welding sputter, grinding of welding seams and welding seam overlaps in accordance with DIN EN 14879-1.

Blast-clean to surface degree Sa 2 ½ according to ISO 12944, part 4.

Free from dirt, grease and oil.

Average surface roughness Rz ≥ 50 µm.

Stainless steel and aluminium:

Cleaning and homogeneous roughening by means of sweep blasting, ISO 12944-4 with non-metallic blasting abrasives.

Average surface roughness Rz ≥ 50 µm.

MIXING

Stir component A mechanically before mixing. Add components A+B carefully in the prescribed mixing ratio before processing. To prevent splashing or spilling of the liquid, combine the components with a variable-speed electric mixer (stepless regulation) at a low

speed for a short period. Then increase the speed to maximum 300 rpm for intensive mixing. The mixing duration is at least 3 minutes and is complete when the two components have combined to form an homogeneous mixture. Decant the mixture into a clean container and mix again once more as described above. Wear suitable safety gloves, a rubber apron, a long-sleeved top, work trousers and tightly-fitting safety goggles/face guard when mixing and decanting the products.

Instruction on initial filling

Before filling the coated tanks or pipes for the first time with potable water or foodstuffs, purging or rinsing with water for at least 1 day.

APPLICATION

The specified dry layer thickness is achieved using the airless-spraying process. Achieving a standard layer thickness and even appearance depends on the application process. Spray applications generally produce the best results. If applying with a paintbrush or roller, further application may be required to achieve the necessary coating thickness depending on the design, local conditions and colour. It is good practice before starting the coating application to test a sample area to determine whether the results of the selected application process meet your requirements with the product in question.

Do not thin SikaCor®-146 DW!

Brush or roller:

- Any bubbles should be removed with a flat surface brush
- Several applications (usually 3) are necessary in order to reach the layer thickness of 400 µm
- On a mineral substrate the first coat of SikaCor®-146 DW must be applied manually. Taking care that SikaCor®-146 DW is worked well into the substrate when

doing this. This is usually done with a flat surface brush or a paintbrush

- The substrate must be pore-free after the application of the first layer

Only mix the quantities which are to be applied in due time.

Consider the fast curing properties of SikaCor®-146 DW!

Airless spraying:

- High performance airless device
- Peak pressure in spray gun at least 180 bar
- Remove sieves. Direct suction (without suction hose)
- Nozzle size 0.48 - 0.58 mm
- Spraying angle e.g. 50°
- Spray hoses ¾", max. 20 m, from spray gun ¼" approx. 2 m
- Material temperature at least + 20°C
- At low temperatures we recommend the insulation of the spray hose as well as the use of a continuous flow heater, particularly in case of long spray hoses

Repair:

- Clean flaws or damaged areas, grind or sweep-blast overlapping areas to a matt finish and clean off all traces of dust
- Overcoat immediately afterwards

CLEANING OF EQUIPMENT

Removal of fresh remnants from tools and application equipment can be carried out using Sika® Thinner E+B immediately after use. Hardened / cured material can only be mechanically removed.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Hellas ABEE

15 Protomagias Str.
14568 Kryoneri
Attica-Greece
Tel.: +30 210 8160 600
Fax: +30 210 8160 606
www.sika.gr | sika@gr.sika.com



Product Data Sheet
SikaCor®-146 DW
July 2018, Version 04.01
020602000270000026

SikaCor-146DW-en-GR-(07-2018)-4-1.pdf