

PRODUCT DATA SHEET

Sikafloor®-356 N

Polyurethane clear matt finish seal coat

DESCRIPTION

Sikafloor®-356 N is a 2-part, clear, solvent-based, polyurethane, low-yellowing, chemical resistant, matt finish seal coat. For normal - medium wear conditions. Internal and external use.

USES

Sikafloor®-356 N may only be used by experienced professionals.

Matt finish seal coat for:

- Sikafloor® flooring systems
- Sikafloor® broadcast and sealed screeds in dry processing areas

CHARACTERISTICS / ADVANTAGES

- For dry processing areas
- Tough-elastic
- Good mechanical and chemical resistance
- Low-yellowing
- Easy applied by roller
-

APPROVALS / STANDARDS

- CE Marking and Declaration of Performance to EN 1504-2 - Surface protection product for concrete - Coating
- CE Marking and Declaration of Performance to EN 13813 - Resin screed material for internal use in buildings
- Decontamination Ability DIN 25 415-1, Sikafloor®-356 N, Forschungszentrum Jülich GmbH, Test report No. 430.16.99.wü2

PRODUCT INFORMATION

Chemical Base	Solvented polyurethane	
Packaging	Part A	8 kg container
	Part B	2 kg container
	Part A+B	10 kg ready to mix unit
	Refer to current price list for packaging variations	
Appearance / Colour	Clear liquid	
Shelf Life	6 months from date of production	
Storage Conditions	The product must be stored properly in original, unopened and undamaged sealed packaging, in dry conditions at temperatures between +5 °C and +30 °C.	
Density	Part A	~1,13 kg/l (DIN EN ISO 2811-1)
	Part B	~0,89 kg/l
	Mixed resin	~0,97 kg/l

All Density values at +23 °C

Product Declaration	EN 1504-2: Surface protection product for concrete - Coating EN 13813: Resin screed material for internal use in buildings
----------------------------	---

TECHNICAL INFORMATION

Chemical Resistance	Resistant to many chemicals. Contact Sika Technical Services for additional information.
Systems	Sikafloor®-356 N can be used with the following: <ul style="list-style-type: none">▪ Sikafloor® smooth epoxy or polyurethane coatings▪ Sikafloor® broadcast systems▪ Sikafloor® epoxy or polyurethane screeds

APPLICATION INFORMATION

Mixing Ratio	Part A : Part B = 80 : 20 (by weight)																
Consumption	Seal coat on Sikafloor® smooth substrates ~0,1–0,15 kg/m ² Seal coat on Sikafloor® broadcast substrates ~0,15–0,3 kg/m ² General These figures are theoretical and do not allow for any additional material due to surface porosity, surface profile, variations in level or wastage etc.																
Ambient Air Temperature	+10 °C min. / +30 °C max.																
Relative Air Humidity	80 % max.																
Dew Point	Beware of condensation. The substrate and uncured applied floor must be at least +3 °C above dew point to reduce the risk of condensation or blooming on the floor finish.																
Substrate Temperature	+10 °C min. / +30 °C max.																
Substrate Moisture Content	Surface of broadcast system to be sealed must be dry																
Pot Life	<table><thead><tr><th><u>Temperature</u></th><th><u>Time</u></th></tr></thead><tbody><tr><td>+10 °C</td><td>~120 minutes</td></tr><tr><td>+20 °C</td><td>~60 minutes</td></tr><tr><td>+30 °C</td><td>~20 minutes</td></tr></tbody></table>	<u>Temperature</u>	<u>Time</u>	+10 °C	~120 minutes	+20 °C	~60 minutes	+30 °C	~20 minutes								
<u>Temperature</u>	<u>Time</u>																
+10 °C	~120 minutes																
+20 °C	~60 minutes																
+30 °C	~20 minutes																
Waiting Time / Overcoating	Before applying Sikafloor®-356 N on Sikafloor®-264 N, 381, 359, 378 allow: <table><thead><tr><th><u>Substrate temperature</u></th><th><u>Minimum</u></th><th><u>Maximum</u></th></tr></thead><tbody><tr><td>+10 °C</td><td>48 hours</td><td>3 days</td></tr><tr><td>+20 °C</td><td>24 hours</td><td>2 days</td></tr><tr><td>+30 °C</td><td>16 hours</td><td>2 days</td></tr></tbody></table> <p>Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.</p>	<u>Substrate temperature</u>	<u>Minimum</u>	<u>Maximum</u>	+10 °C	48 hours	3 days	+20 °C	24 hours	2 days	+30 °C	16 hours	2 days				
<u>Substrate temperature</u>	<u>Minimum</u>	<u>Maximum</u>															
+10 °C	48 hours	3 days															
+20 °C	24 hours	2 days															
+30 °C	16 hours	2 days															
Applied Product Ready for Use	<table><thead><tr><th><u>Temperature</u></th><th><u>Foot traffic</u></th><th><u>Light traffic</u></th><th><u>Full cure</u></th></tr></thead><tbody><tr><td>+10 °C</td><td>~36 hours</td><td>~5 days</td><td>~10 days</td></tr><tr><td>+20 °C</td><td>~24 hours</td><td>~3 days</td><td>~7 days</td></tr><tr><td>+30 °C</td><td>~16 hours</td><td>~2 days</td><td>~3 days</td></tr></tbody></table> <p>Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.</p>	<u>Temperature</u>	<u>Foot traffic</u>	<u>Light traffic</u>	<u>Full cure</u>	+10 °C	~36 hours	~5 days	~10 days	+20 °C	~24 hours	~3 days	~7 days	+30 °C	~16 hours	~2 days	~3 days
<u>Temperature</u>	<u>Foot traffic</u>	<u>Light traffic</u>	<u>Full cure</u>														
+10 °C	~36 hours	~5 days	~10 days														
+20 °C	~24 hours	~3 days	~7 days														
+30 °C	~16 hours	~2 days	~3 days														

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

The applied broadcast resin floor (epoxy, polyurethane, polyurea-hybrid and polyurea resin) surface must be tack free, clean and dry.

If dust exists on the surface, it must be completely removed before application of the product, preferably by vacuum extraction equipment.

MIXING

Prior to mixing all parts, mix Part A (resin) using a low speed single paddle electric stirrer (300 - 400 rpm) or other suitable equipment to mix liquid and all the coloured pigment until a uniform colour / mix has been achieved. Add Part B (hardener) to Part A and mix Part A + B continuously for 3,0 minutes until a uniformly coloured mix has been achieved. To ensure thorough mixing pour materials into a clean container and mix again for at least 1,0 minute to achieve a smooth consistent mix. Excessive mixing must be avoided to minimise air entrainment. During the final mixing stage, scrape down the sides and bottom of the mixing container with a straight edge trowel or spatula at least once to ensure complete mixing. Mix full units only. Mixing time for A+B = ~4,0 minutes.

APPLICATION

Strictly follow installation procedures as defined in method statements, application manuals and working instructions which must always be adjusted to the actual site conditions.

Prior to application, confirm substrate moisture content, relative air humidity, dew point, substrate, air and product temperatures.

After waiting the appropriate overcoating time, pour the mixed Sikafloor®-356 N onto the existing resin layer and spread evenly using a short piled nylon roller in two directions at right angles to each other.

General

A seamless finish can be achieved if a 'wet' edge is maintained during application.

CLEANING OF TOOLS

Clean all tools and application equipment with Thinner C immediately after use. Hardened material can only be removed mechanically.

FURTHER DOCUMENTS

- Sika Method Statement: Evaluation and Preparation of Surfaces for Flooring Systems
- Sika Method Statement: Mixing & Application of Flooring Systems
- Sika® Method Statement: Sikafloor®-Cleaning Regime

LIMITATIONS

- Freshly applied Sikafloor®-356 N must be protected from damp, condensation and water for at least 24 hours.
- Uncured material reacts in contact with water (foaming). During application care must be taken that no sweat drips into the fresh Sikafloor®-356 N. Wear head and wrist bands.
- Apply Sikafloor®-356 N to tack free Sikafloor®-264 N or 381, 359, 378
- Unevenness of the substrate and inclusions of dirt cannot be covered by thin sealer coats. Therefore the substrate and adjacent areas must be cleaned thoroughly prior to application.
- If temporary heating is required do not use gas, oil, paraffin or other fossil fuel heaters, these produce large quantities of both CO₂ and H₂O water vapour, which may adversely affect the finish. For heating use only electric powered warm air blower systems.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

DIRECTIVE 2004/42/CE - LIMITATION OF EMISSIONS OF VOC

According to the EU Directive 2004/42/CE, the maximum allowed content of VOC (product category IIA / j type SB) is 500 g/l (Limits 2010) for the ready to use product.

The maximum content of Sikafloor®-356 N is < 500 g/l VOC for the ready to use product.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

Sika South Africa (Pty) Ltd

9 Hocking Place,
Westmead, 3608
South Africa
Phone +27 31 792 6500
www.sika.co.za



Product Data Sheet

Sikafloor®-356 N
August 2020, Version 01.02
020812050030000008

Sikafloor-356N-en-ZA-(08-2020)-1-2.pdf