



TECNOPLASTIC F - PLASTIC CHARGES FOR ANTISLIP FINISH

TECNOPLASTIC F is a kind of micronized plastic (polyamide) for texturing polyurethane resins, and achieve antislip surfaces for flooring.

USES

- for mix with polyurethane resins TECNOTOP 2C, TECNOTOP 2CP, TECNOTOP 1C to achieve a level of medium-high roughness (depending on the mixing ratio). Applied in our waterproofing and flooring systems.

consumption	5 ~ 8 % depending on the texture desired
medium size of particle	125 µm (0,125 mm.)



GENERAL FEATURES

- TECNOPLASTIC F is a coarse powder for producing significant surface texturing. The nature and degree of texturing depend on the applied film thickness and the ratio of texturing agent to binder.
- To mix with TECNOTOP range of aliphatic resins
- This allows the optical and functional properties of a surface to be tailored to specific applications.
- Conforming even to norm ENV 12633: (floors slipperiness), to achieve Class 3 (>45 slip resistance), depending on dosage (consult our technical department).
- Depending on the formulation TECNOPLASTIC F may tend to sediment during storage of the coating. In such cases employing an anti-settling agent is necessary.
- The thermal stability is influenced by the binder and also depends on the duration of exposure. Experiments must be undertaken to precisely determine the thermal stability if long-term exposure to temperatures of more than 140 °C is expected.
- TECNOPLASTIC F can be used in both solvent-based and solvent-free coatings, and also in water-based coating systems. The areas of application include decorative coatings and anti-slip coatings.
-



TECNOPLASTIC F is resistant to most customary solvents, but this should be checked when testing the overall coating formulation.

PACKAGING

Metal tins of 2 kg.



SHELF LIFE

TECNOPLASTIC F can be stored for at least 24 months at room temperature under dry conditions.

APPLICATION METHOD

The application method of TECNOPLASTIC F is:

- Mix the desired dosage in the A component of TECNOTOP 2C / 2CP / 1C. The amount to be added in each case will depend on the desired or required texture project, this action can be performed by a speed-stirrer. It does not require the use of added agents, even if water-based systems are used. Perform this action until a homogeneous mixture.
- In systems containing PIGMENTS, texturing agents must be added after grinding these ones

HANDLING

According to Regulation (EC) No. 1272/2008, TECNOPLASTIC F is not classified as a dangerous product and therefore does not need to be labeled. Due to the powdery nature of the product, measures for dust protection must be heeded and the build-up of electrostatic charge must be avoided.

Consult the material and safety data sheet of the product (MSDS).

PHYSICAL DATA

- appearance: white powder
- bulk weight: ± 640 g/l
- density: $\pm 1,22$ g/cm³
- melting range: $\pm 150-160$ °C
- particle size:
 - d50 ± 150 μ m,
 - d90 ± 225 μ m,
 - d99,9 ± 280 μ m

NOTICE: While all the information presented in this document is believed to be reliable and to represent the best available data on these products, do not constitute sales specifications. The product properties may be changed without notice. NOTHING HEREIN IS TO BE CONSTRUED AS A WARRANTY, EXPRESS OR OTHERWISE. IN ALL CASES, IT IS THE RESPONSIBILITY OF THE USER TO DETERMINE THE APPLICABILITY OF SUCH INFORMATION AND RECOMMENDATIONS AND THE SUITABILITY OF ANY PRODUCT FOR ITS OWN PARTICULAR PURPOSE. Liability of Tecnopol Sistemas and its affiliates for all claims is limited to the purchase price of the material. Products may be toxic and require special precautions in handling. User should obtain detailed information on toxicity, together with proper shipping, handling and storage procedures, and comply with all applicable safety and environmental standards. No freedom from any patents or other industrial or intellectual property rights is granted or to be inferred.

