

## TECHNICAL SHEET 01.07-eng

### PRIMERS

# JUBOSIL GF

Adhesion improving primer

## 1. Description, Application

JUBOSIL GF is a white covering wall paint based on polymeric binders. It is used as a **primer on interior wall surfaces before they are painted with silicate or less covering acrylic and other dispersion paints.**

**It enables adhesion of silicate paints also to concrete, gypsum renders, gypsum-cardboards** and old, well-adhered, non-shiny dispersion coats. **It covers various types of water-insoluble stains well.** It equalises the surfaces with regard to water absorption, slightly reinforces it and binds dust and other badly-adhered particles, which could not have been removed with cleaning for whatever reason.

## 2. Packaging and Colour Shades

Plastic containers holding 5 liters:  
White (shade 1001)

## 3. Technical Data

|   |                                   |   |
|---|-----------------------------------|---|
| Density (kg/dm <sup>3</sup> )   |                                   | ~1.65   |
| Drying time<br>T = +20 °C, relative<br>air humidity = 65 %<br>(hours) | Touch dry                         | ~2  |
|   | Suitable for<br>further treatment | ~12   |
| Content of vaporous organic substances (VOS) (g/l)                    |                                   | <5<br>The EU VOS requirement – category A/g<br>(from 1 January 2010): <30 |

Main ingredients: styrene-acrylate binder, calcite and aluminosilicate fillers, cellulose thickening agent, titanium dioxide, water

## 4. Surface Preparation

Surfaces include interior wall and ceiling surfaces – fine lime, lime-cement or cement renders, concrete, gypsum-cardboards, fibre-cement boards, chipboards and decorative renders of all types that are not too rough. In any event, the surface should be solid, dry, and without any badly-adhered particles, dust, remains of paneling oils, fat or other filth.

In normal conditions (T = +20 °C, relative air humidity = 65 %), dry or mature the newly applied renders and levelling compounds for at least a day for each mm of their thickness. Dry concrete surfaces for at least a month. In case of paint renovation, thoroughly remove from the surface all old badly-adhered coatings, slurries and other decorative coats, all of which get easily soaked in water.

In the event of potential mending of façade surfaces that have been damaged in any way, follow only procedures, which ensure, concerning roughness, as high a level of equalisation as possible to the mended surface.

## 5. Instruction for Use

Prior to application, stir the product well and dilute it with water up to 10 %. Quantities necessary to coat individual surfaces are calculated or estimated on the basis of the area of these surfaces and data on consumption rate, and, in specific cases, consumption is determined by making measurements on a test surface that is large enough.



Apply the primer normally in one coat using one of the following: a long-bristle fur or textile painting roller (length of hairs or threads is 18 to 20 mm; the following can be used: natural and artificial fur or textile linings made of different synthetic threads – polyamide, dralon, vestan, nylon, perlon or polyester), a paint brush suitable for the application of dispersion coats or spray it. When applying the paint with a roller, use a suitable bucket grid.

The primer can be sprayed onto a surface with traditional high pressure and modern low pressure spray guns of different types (with “external” or “internal mixing of air”), as well as airless aggregates of a variety of manufactures. As regards to the choice of diameter of spraying nozzles and service pressure, follow the producer’s instructions. Paint an individual wall surface without any interruptions from one corner of the wall to the other. Always treat surfaces inaccessible to a standard long-bristle paint roller or a spray gun (corners, gutters, narrow reveal surfaces, and similar) first using suitable brushes or smaller paint rollers adjusted to existing conditions.

The application is possible only in suitable microclimate conditions: the temperature of the air and the wall surface should be between +5°C and +35°C and the relative air humidity should be below 80 %.

|   |                            |
|---|----------------------------|
| Indicative or average use (depending on absorption and roughness of the surface): |                            |
| JUBOSIL GF  | 130 - 150 g/m <sup>2</sup> |

## 6. Tool Cleaning, Waste Management

Thoroughly clean the tools with water immediately after use. Dried stains cannot be removed.

Keep unused primer (only the one that has not been diluted!) in a well sealed packaging for potential repairs or later use. Waste liquid remains must not be emptied into drains, watercourses, or environment and they must not be disposed together with domestic wastes. Mix them with cement (hardened mortar remains and wastes, sand or sawdust may be added to them) and when they harden, deposit them onto the dumping grounds of construction waste (waste classification number: 17 09 04) or municipal waste (waste classification number: 08 01 12).

Cleaned packaging can be recycled.

## 7. Safety at Work

Respiratory protection with a protective mask and protection of eyes with protective glasses or with a safety mask is necessary only when applying the primer by spraying. Otherwise follow general instructions and regulations on safety of construction work or works including paintwork. When the primer is applied with a paint roller or a brush, the use of special personal protection means and the application of special measures for safe use are not necessary.

In case of contact with eyes, rinse with water immediately.

## 8. Storage, Transportation Conditions and Durability

Storage and transportation at temperatures between +5°C and +25°C, protected from direct sunlight, out of the reach of children, IT MUST NOT FREEZE!

Shelf life when stored in an originally sealed and undamaged packaging: at least 12 months.

## 9. Quality Control

The product’s quality characteristics are determined by the internal manufacturing specifications as well as by the Slovenian, European and other standards. JUB ensures achieving of the declared or set quality level by the ISO 9001 system for total quality management and control, which has been implemented at JUB for many years and which comprises daily quality checks in its own laboratories, occasionally at the ZAG Construction Institute in Ljubljana and other independent expert institutions in Slovenia and abroad. During the manufacturing process, JUB strictly complies with the Slovenian and European standards for protection of the environment and for ensuring security and health at work, which is confirmed by the ISO 14001 and OHSAS 18001 certificates.

## 10. Other Information

The technical instructions in this brochure are given based on JUB’s experience and are given as a guideline for achieving optimum results. JUB cannot accept any responsibility for the damage caused by incorrect selection of a product, incorrect use or unprofessional work.

This technical sheet supplements and replaces all preceding editions. JUB reserves the right to change and



supplement data in the future.

Denomination and date of publishing: **TRC-1041/09-bg-at**, 30.12.2009

---

JUB kemična industrija d.o.o.,  
Dol pri Ljubljani 28, 1262 Dol pri Ljubljani, SLOVENIA  
Phone: (01) 588 41 00 Main Reception Desk,  
(01) 588 42 17 Sales Department,  
(01) 588 42 18 or 080/15 56 Technical Support  
Fax: (01) 588 42 50 Sales department  
e-mail: [jub.info@jub.si](mailto:jub.info@jub.si)  
Web page: [www.jub.eu](http://www.jub.eu)

